



SPECIFICATION

(Reference sheet)

· Supplier : Samsung electro-mechanics · Samsung P/N : CL31A106KPHNNNF


Product : Multi-layer Ceramic Capacitor Description : CAP, 10uF, 10V, ±10%, X5R, 1206

A. Samsung Part Number

<u>CL</u> <u>31</u> <u>A</u> <u>106</u> <u>K</u> <u>P</u> <u>H</u> <u>N</u> <u>N</u> <u>N</u> <u>F</u> 1 2 3 4 5 6 7 8 9 10 11

1	Series	Samsung Multi-layer Ceramic Capacitor				
2	Size	1206 (inch code)	L: 3.20	± 0.20 mm	W:	$1.60 \pm 0.20 \text{ mm}$
3	Dielectric	X5R	8	Inner electrode		Ni
4	Capacitance	10 uF		Termination		Cu
(5)	Capacitance	±10 %		Plating		Sn 100% (Pb Free)
	tolerance		9	Product		Normal
6	Rated Voltage	10 V	10	Special		Reserved for future use
7	Thickness	1.60 ± 0.20 mm	11)	Packaging		Embossed Type, 13" reel

B. Structure & Dimension



Samsung P/N	Dimension(mm)					
Samsung F/N	L	W	Т	BW		
CL31A106KPHNNNF	3.20 ± 0.20	1.60 ± 0.20	1.60 ± 0.20	0.50 ± 0.30		

C. Samsung Reliablility Test and Judgement Condition

A capacitor prior to measuring the capacitance is heat treated at 150°C+0/-10°C for 1 hour and maintained in ambient air for 24±2 hours. Insulation		Judgement	Test condition		
Tan δ (DF) 0.05 max. treated at 150°C+0/-10°C for 1 hour and maintained in ambient air for 24±2 hours. Insulation 10,000Mohm or 100Mohm×μF Rated Voltage 60~120 sec. Resistance Whichever is smaller Agreamance Microscope (×10) Appearance No abnormal exterior appearance Microscope (×10) Withstanding No delectric breakdown or mechanical breakdown 250% of the rated voltage Temperature X5R (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder Soldering Heat Tan δ, IR: initial spec. Solder pot: 270±5°C, 10±1sec. Vibration Test Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change: within ±12.5% With rated voltage Resistance Tan δ, IR: initial spec. With 150% of the rated vol	Capacitance	Within specified tolerance	1kHz ±10% / 1.0±0.2Vrms		
Resistance Whichever is smaller Microscope (×10) Appearance No abnormal exterior appearance Microscope (×10) Withstanding No dielectric breakdown 250% of the rated voltage Voltage mechanical breakdown Temperature X5R Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength No peeling shall be occur on the of Termination 500g·f, for 10±1 sec. Gramination Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 24±5±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan 5, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibitation Test Capacitance change: within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ: 0.125 max IR: Max. operating temperature High Temperature Capacitance change: within ±12.5% With 150% of	Tan δ (DF)	0.05 max.	treated at 150 °C+0/-10 °C for 1 hour and maintained in		
Appearance No abnormal exterior appearance Microscope (×10) Withstanding Voltage No dielectric breakdown 250% of the rated voltage Temperature Characteristics KF Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·ft, for 10±1 sec. Bending Strength of Termination With 1.0mm/sec. Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change : within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.125 max IR : 500Mohm or 12.5Mohm × //F Whichever is smaller With 150% of the rated voltage Max. operating temperature Max. operating temperature Resistance Tan δ : 0.125 max Within ±17.5% With 100+48/-0hrs To 00+48/-0hrs Temperature Cycling Capacitance change : within	Insulation	10,000Mohm or 100Mohm× <i>μ</i> F	Rated Voltage 60~120 sec.		
Withstanding Voltage No dielectric breakdown or mechanical breakdown 250% of the rated voltage Temperature Characteristics X5R Characteristics (From-55°C to 85°C, Capacitance change should be within ±15%) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245£5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change: within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ: 0.125 max IR: 500Mohm or 12.5Mohm × /F Whichever is smaller With 150% of the rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs High Temperature Resistance Capacitance change: within ±12.5% With 150% of the rated voltage 40±2°C, 90~95%RH, 500+48/-0hrs Max. operating temperature 40±0°C Amax. ope	Resistance	Whichever is smaller			
Voltage mechanical breakdown Temperature Characteristics X5R Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±6°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change: within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ: 0.125 max IR: 500Mohm or 12.5Mohm × μF Whichever is smaller With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs High Temperature Capacitance change: within ±7.5% Vith 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Capacitance change: within ±7.5% I cycle condition Nin. operating temperature 25°C Amx. operating temperature 25°C	Appearance	No abnormal exterior appearance	Microscope (×10)		
Temperature Characteristics Characteristics Adhesive Strength of Termination Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Soldering Heat Tan δ, IR: initial spec. Capacitance change: within ±5% Tan δ 1.25 max IR: 5000Mohm or 12.5Mohm × μF Whichever is smaller High Temperature Resistance Cycling Tan δ, IR: initial spec. X5R No peeling shall be occur on the of Terminal surface within ±12.5% Solder of 10±1 sec. Sology f, for 10±1 sec. Sology f, for 10±1 sec. Solder shall spec. SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Solder pot: 270±5°C, 10±1sec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs IR: 5000Mohm or 12.5Mohm × μF Whichever is smaller High Temperature Capacitance change: within ±12.5% Tan δ 0.125 max IR: 1,000Mohm or 25Mohm × μF Whichever is smaller Capacitance change: within ±7.5% Tan δ, IR: initial spec. Tan δ, I	Withstanding	No dielectric breakdown or	250% of the rated voltage		
Characteristics (From-55℃ to 85℃, Capacitance change should be within ±15%) Adhesive Strength of Termination No peeling shall be occur on the terminal electrode 500g·f, for 10±1 sec. Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5℃, 3±0.3sec. (preheating : 80~120℃ for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5℃, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change : within ±12.5% Within ±12.5% Within *12.5% Within *10.0mm/sec. Moisture Capacitance change : within ±12.5% Within *2.5% Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Woldstare Tan δ : 0.125 max Within ±12.5% Within *10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Within Temperature Capacitance change : within ±12.5% Within ±10.5% Within ±10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Within Temperature Capacitance change : within ±12.5% Within ±10.5% Within ±10Hz to 55H	/oltage mechanical breakdown				
Adhesive Strength of Termination Bending Strength Of Termination Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly Capacitance change: within ±7.5% Solder pot: 270±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±5% Amplitude: 1.5mm From 10lz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change: within ±12.5% With rated voltage Resistance Tan δ: 0.125 max IR: 500Mohm or 12.5Mohm × μF Whichever is smaller High Temperature Resistance Tan δ: 0.125 max IR: 1,000Mohm or 25Mohm × μF Whichever is smaller Temperature Capacitance change: within ±7.5% With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Min. operating temperature Capacitance change: within ±7.5% To cycle condition Min. operating temperature → 25°C Max. operating temperature → 25°C Max. operating temperature → 25°C Max. operating temperature → 25°C	Temperature	X5R			
of Termination terminal electrode Bending Strength Capacitance change: within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0cu0.5 solder 245±5°C, 3±0.3sec. (preheating: 80~120°C for 10~30sec.) Resistance to Capacitance change: within ±7.5% Solder pot: 270±5°C, 10±1sec. Soldering Heat Tan δ, IR: initial spec. Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change: within ±12.5% Tan δ: 0.125 max IR: 500Mohm or 12.5Mohm × μF Whichever is smaller With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs High Temperature Resistance Capacitance change: within ±12.5% With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Cycling Capacitance change: within ±7.5% Min. operating temperature 35°C Amax. Operating temperature 35°C Ama	Characteristics	(From-55℃ to 85℃, Capacitance change sl	hould be within ±15%)		
Bending Strength Capacitance change : within ±12.5% Bending to the limit (1mm) with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Wibration Test Capacitance change : within ±12.5% With rated voltage Moisture Capacitance change : within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.125 max IR : 500Mohm or 12.5Mohm × μF Whichever is smaller With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Resistance Tan δ : 0.125 max IR : 1,000Mohm or 25Mohm × μF Whichever is smaller 1 cycle condition Min. operating temperature → 25°C → Max. operating temperature → 25°C → Max. operating temperature → 25°C	Adhesive Strength	No peeling shall be occur on the	500g·f, for 10±1 sec.		
with 1.0mm/sec. Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Soldering Heat Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Vibration Test Capacitance change : within ±5% Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Resistance Capacitance change : within ±12.5% Tan δ : 0.125 max IR : 500Mohm or 12.5Mohm × μF With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs High Temperature Resistance Capacitance change : within ±12.5% Tan δ : 0.125 max IR : 1,000Mohm or 25Mohm × μF With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Cycling Capacitance change : within ±7.5% Tan δ, IR : initial spec. 1 cycle condition Min. operating temperature → 25°C → Max. operating temperature → 25°C	of Termination	terminal electrode			
Solderability More than 75% of terminal surface is to be soldered newly SnAg3.0Cu0.5 solder 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.) Resistance to Capacitance change : within ±7.5% Solder pot : 270±5°C, 10±1sec. Soldering Heat Tan δ, IR : initial spec. Amplitude : 1.5mm Vibration Test Capacitance change : within ±5% Tan δ, IR : initial spec. Amplitude : 1.5mm From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.125 max IR : 500Mohm or 12.5Mohm × μF Whichever is smaller With 150% of the rated voltage Max. operating temperature Resistance Tan δ : 0.125 max IR : 1,000Mohm or 25Mohm × μF Whichever is smaller Vith 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Capacitance change : within ±7.5% Whichever is smaller 1 cycle condition Min. operating temperature → 25°C Cycling Tan δ, IR : initial spec. Max. operating temperature → 25°C	Bending Strength	Capacitance change : within ±12.5%	Bending to the limit (1mm)		
is to be soldered newly 245±5°C, 3±0.3sec. (preheating : 80~120°C for 10~30sec.)			with 1.0mm/sec.		
Resistance to Soldering Heat Tan δ, IR: initial spec. Vibration Test Capacitance change: within ± 5% Tan δ, IR: initial spec. Within ± 5% Tan δ, IR: initial spec. Capacitance change: within ± 5% Tan δ, IR: initial spec. Moisture Resistance Capacitance change: within ± 12.5% Tan δ: 0.125 max IR: 500Mohm or 12.5Mohm × Whichever is smaller High Temperature Resistance Resistance Resistance Tan δ: 0.125 max IR: 1,000Mohm or 25Mohm × IR: 1,000Mohm or 25Mohm × With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Capacitance change: within ±7.5% Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ, IR: initial spec. Vithin ± 12.5% Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Vithin ±7.5% Temperature Cycling Tan δ, IR: initial spec. Vithin ±7.5% Max. operating temperature Amaz. operating temperature Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) Amplitude: 1.5	Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder		
Resistance to Capacitance change : within $\pm 7.5\%$ Solder pot : $270\pm 5^{\circ}$ C, 10 ± 1 sec. Vibration Test Capacitance change : within $\pm 5\%$ Tan δ , IR : initial spec. Vibration Test Capacitance change : within $\pm 5\%$ Tan δ , IR : initial spec. Moisture Capacitance change : within $\pm 12.5\%$ Resistance Tan δ : 0.125 max IR : 500 Mohm or 12.5 Mohm × \cancel{L}° Whichever is smaller High Temperature Resistance Tan δ : 0.125 max IR : $1,000$ Mohm or 25 Mohm × \cancel{L}° With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Capacitance change : within $\pm 7.5\%$ Mix. operating temperature $\rightarrow 25^{\circ}$ C $\rightarrow Max$. operating temperature $\rightarrow 25^{\circ}$ C		is to be soldered newly	245±5°C, 3±0.3sec.		
Soldering HeatTan δ , IR: initial spec.Amplitude: 1.5mm From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z)MoistureCapacitance change: Tan δ : 0.125 max IR: 500Mohm or 12.5Mohm × μ F Whichever is smallerWithin ±12.5% 40±2°C, 90~95%RH, 500+12/-0hrsHigh Temperature ResistanceCapacitance change: Tan δ : 0.125 max IR: 1,000Mohm or 25Mohm × μ F Whichever is smallerWith 150% of the rated voltage Max. operating temperature 1,000+48/-0hrsTemperature CyclingCapacitance change: Within ±7.5%Within ±7.5% Tan δ , IR: initial spec.1 cycle condition Min. operating temperature Min. operating temperatureTan δ , IR: initial spec.Min. operating temperature Min. operating temperature \rightarrow 25°C \rightarrow Max. operating temperature			(preheating : 80~120°C for 10~30sec.)		
Vibration Test Capacitance change : Tan δ, IR : initial spec. within ± 5% From 10Hz to 55Hz (return : 1min.) 2hours × 3 direction (x, y, z) Moisture Capacitance change : within ±12.5% With rated voltage 40±2°C, 90~95%RH, 500+12/-0hrs Resistance Tan δ : 0.125 max IR : 500Mohm or 12.5Mohm × μ F Whichever is smaller With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Resistance Tan δ : 0.125 max IR : 1,000Mohm or 25Mohm × μ F Whichever is smaller With 150% of the rated voltage Max. operating temperature 1,000+48/-0hrs Temperature Capacitance change : within ±7.5% Whichever is smaller 1 cycle condition Min. operating temperature → 25°C → Max. operating temperature → 25°C → Max. operating temperature → 25°C	Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5°C, 10±1sec.		
Tan δ , IR: initial spec. From 10Hz to 55Hz (return: 1min.) 2hours × 3 direction (x, y, z) Moisture Resistance Tan δ : 0.125 max IR: 500Mohm or 12.5Mohm × μ F Whichever is smaller Capacitance change: within ±12.5% With rated voltage $40\pm2^{\circ}\text{C}$, $90\sim95\%$ RH, $500+12\text{J-0hrs}$ High Temperature Resistance Tan δ : 0.125 max IR: 1,000Mohm or 25Mohm × μ F Whichever is smaller Temperature Capacitance change: within ±7.5% Whichever is smaller Temperature Capacitance change: within ±7.5% Tan δ , IR: initial spec.	Soldering Heat	Tan δ, IR : initial spec.			
Resistance Tan δ : 0.125 max $40\pm2^{\circ}$ C, $90\sim95\%$ RH, $500+12/-0$ hrs High Temperature Capacitance change : within ±12.5% With 150% of the rated voltage Resistance Max. operating temperature IR : 1,000Mohm or 25Mohm × μF 1,000+48/-0hrs Temperature Capacitance change : within ±7.5% 1 cycle condition Cycling Tan δ, IR : initial spec. Max. operating temperature → 25°C → Max. operating temperature → 25°C	Vibration Test	1 '	From 10Hz to 55Hz (return : 1min.)		
IR : 500Mohm or 12.5Mohm × μ F Whichever is smaller	Moisture	Capacitance change: within ±12.5%	With rated voltage		
Whichever is smaller High Temperature Capacitance change : within ±12.5% With 150% of the rated voltage Resistance Tan δ : 0.125 max Max. operating temperature IR : 1,000Mohm or 25Mohm × μ F 1,000+48/-0hrs Whichever is smaller Capacitance change : within ±7.5% 1 cycle condition Cycling Tan δ, IR : initial spec. Min. operating temperature → 25°C → Max. operating temperature → 25°C	Resistance	Tan δ: 0.125 max	40±2°C, 90~95%RH, 500+12/-0hrs		
Resistance Tan δ : 0.125 max Max. operating temperature IR : 1,000Mohm or 25Mohm × μ F 1,000+48/-0hrs Whichever is smaller 1 cycle condition Cycling Tan δ, IR : initial spec. Min. operating temperature Min. operating temperature → 25°C → Max. operating temperature → 25°C					
IR: 1,000Mohm or 25Mohm × μ F Whichever is smaller Temperature Cycling Capacitance change: within ±7.5% Tan δ , IR: initial spec. Min. operating temperature Max. operating temperature \rightarrow 25°C \rightarrow Max. operating temperature \rightarrow 25°C	High Temperature	Capacitance change: within ±12.5%	With 150% of the rated voltage		
	Resistance	Tan δ: 0.125 max	Max. operating temperature		
Cycling Tan δ, IR : initial spec. Min. operating temperature → 25°C → Max. operating temperature → 25°C			1,000+48/-0hrs		
→ Max. operating temperature → 25°C	Temperature	Capacitance change: within ±7.5%	1 cycle condition		
	Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25°C		
5 cycle test			ightarrow Max. operating temperature $ ightarrow$ 25°C		
			5 cycle test		

^{**} The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method:

Reflow (Reflow Peak Temperature : 260±5°C, 30sec.)



Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

Disclaimer & Limitation of Use and Application

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury.

We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- ① Aerospace/Aviation equipment
- 2 Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- 4 Military equipment
- ⑤ Disaster prevention/crime prevention equipment
- 6 Power plant control equipment
- Atomic energy-related equipment
- Undersea equipment
- Traffic signal equipment
- Data-processing equipment
- ## Electric heating apparatus, burning equipment
- Safety equipment
- ® Any other applications with the same as or similar complexity or reliability to the applications